



Meteorwave M1 – Dielectric Properties Table

LAMINATE:

| Thickness | & | Tol. | Construction | | | | RC% | 10 GHz Dk | 10 GHz Df |
|-----------|---|--------|--------------|------|--|--|-----|-----------|-----------|
| 0.0030 | ± | 0.0005 | 1 | 1035 | | | 80% | 3.15 | 0.0016 |
| 0.0040 | ± | 0.0005 | 1 | 1078 | | | 75% | 3.23 | 0.0017 |
| 0.0050 | ± | 0.0007 | 1 | 1078 | | | 80% | 3.15 | 0.0016 |
| 0.0060 | ± | 0.0007 | 2 | 1035 | | | 80% | 3.15 | 0.0016 |
| 0.0080 | ± | 0.0007 | 2 | 1078 | | | 75% | 3.23 | 0.0017 |
| 0.0100 | ± | 0.001 | 2 | 1078 | | | 80% | 3.15 | 0.0016 |
| 0.0150 | ± | 0.0015 | 3 | 1078 | | | 80% | 3.15 | 0.0016 |
| 0.0200 | ± | 0.0025 | 4 | 1078 | | | 80% | 3.15 | 0.0016 |
| 0.0300 | ± | 0.004 | 6 | 1078 | | | 80% | 3.15 | 0.0016 |
| 0.0600 | ± | 0.005 | 12 | 1078 | | | 80% | 3.15 | 0.0016 |

The following laminate and prepreg items are a representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For Information:

North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117

agc-ml.digital-sales@agc.com . www.agc-multimaterial.com

November 13, 2024



Meteorwave M1 – Dielectric Properties Table

PREPREG:

| Glass | RC% | 10GHz Dk | 10GHz Df | Thickness (inches) | Thickness (µm) |
|-------|-----|----------|----------|--------------------|----------------|
| 1035 | 80 | 3.15 | 0.0016 | 0.0030 | 75.2 |
| 1078 | 75 | 3.23 | 0.0017 | 0.0039 | 99.0 |
| 1078 | 80 | 3.15 | 0.0016 | 0.0050 | 127.0 |

The following laminate and prepreg items are a representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For Information:

North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117

agc-ml.digital-sales@agc.com . www.agc-multimaterial.com