

TSM-DS3b Dimensionally Stable Low Loss Laminate

TSM-DS3b is a thermally stable, industry leading low loss core (Df = 0.0011 at 10 GHz) that can be manufactured with the predictability and consistency of the best fiberglass reinforced epoxies. TSM-DS3b is a ceramic-filled reinforced material with very low fiberglass content (~ 5%) that rivals epoxies in fabricating large format complex multilayers.

TSM-DS3b was developed for high power applications (thermal conductivity = 0.65 W/M*K) where it is necessary for the dielectric material to conduct heat away from other heat sources in a PWB design. TSM-DS3b was also developed to have very low coefficients of thermal expansion for demanding thermal cycling.

A TSM-DS3b core combined with *fastRise*TM27 (Df = 0.0014 at 10 GHz) prepreg is an industry leading solution for the lowest possible dielectric losses that can be attained at epoxy-like 420 °F fabrication temperatures. The low insertion losses of TSM-DS3b/*fastRise*TM27 are only rivaled by fusion bonding (the melting of pure Teflon® laminates from 550 °F to 650 °F). Fusion bonding is expensive, it causes excessive material movement and it puts stress on plated through holes. For complex multilayers, the price of poor yield drives up the final material cost. *fastRise*TM27 enables the sequential lamination of TSM-DS3b at a low 420 °F with consistency and predictability that reduces cost.

For microwave applications, the low x, y and z CTE values assure that critical spacings between traces in filters and couplers have very low movement with temperature. TSM-DS3b can be used with very low profile copper foils yielding a smooth copper edge between coupled lines.

Registration over many layers is critical for yield and variations in copper weight and copper etching across a panel can cause non-linear movement. Non-linear movement over large panels leads to a lack of registration of the drilled hole to the pad and possibly open circuits.

TSM-DS3b is compatible with Ticer® and OhmegaPly® resistive foils. Resistor foil stability is best achieved when laminating at low temperatures using AGC's *fastRise*TM27 family of prepregs.

TSM-DS3b is intended for RF circuitry and requires OEM design validation for digital circuitry.





Teflon® is a registered trademark of E.I. du Pont de Nemours and Company

Benefits & Applications:


- Industry best Df (Df = 0.0011 @10 GHz)
- High thermal conductivity (0.65 W/M*K)
- Low (~5%) fiberglass content
- Dimensional stability rivals epoxy
- Enables large format high layer count PWBs
- Builds complex PWBs in yield w/ consistency and predictability
- Temperature stable Dk +/- 0.25% (-30 to 120° C)
- Compatible with resistive foils

- Couplers
- Phased Array Antennas
- Radar Manifolds
- mmWave Antenna/Automotive
- Oil Drilling
- Semiconductor/ATE Testing

TSM-DS3b Dimensionally Stable Low Loss Laminate



Insertion loss of TSM-DS3b-0050-ULPH



Microstrip insertion loss of TSM-DS3b-0050 ULPH using Southwest Connectors (11.7 mil trace width).

Southwest: 1892-04A-5 (1.85 mm female end launch, pin .005D, diel. 0.0290D)

TSM-DS3b Typical Values					
Property	Test Method	Unit	Value	Unit	Value
Dk	IPC-650 2.5.5.3		3.00 ± 0.04		3.00 ± 0.04
T _c K (-30 to 120 °C)	IPC-650 2.5.5.5.1 (Modified)	ppm	5.4	ppm	5.4
Df	IPC-650 2.5.5.5.1 (Modified)		0.0011		0.0011
Dielectric Breakdown	IPC-650 2.5.6 (ASTM D 149)	kV	47.5	kV	47.5
Dielectric Strength	ASTM D 149 (Through Plane)	V/mil	548	V/mm	21,575
Arc Resistance	IPC-650 2.5.1	Seconds	226	Seconds	226
Moisture Absorption	IPC-650 2.6.2.1	%	0.07	%	0.07
Flexural Strength (MD)	ASTM D 790/ IPC-650 2.4.4	psi	11,811	N/mm ²	81
Flexural Strength (CD)	ASTM D 790/ IPC-650 2.4.4	psi	7,512	N/mm ²	51
Tensile Strength (MD)	ASTM D 3039/IPC-650 2.4.19	psi	7,030	N/mm ²	48
Tensile Strength (CD)	ASTM D 3039/IPC-650 2.4.19	psi	3,830	N/mm ²	26
Elongation at Break (MD)	ASTM D 3039/IPC-650 2.4.19	%	1.6	%	1.6
Elongation at Break (CD)	ASTM D 3039/IPC-650 2.4.19	%	1.5	%	1.5
Young's Modulus (MD)	ASTM D 3039/IPC-650 2.4.19	psi	973,000	N/mm ²	6,708
Young's Modulus (CD)	ASTM D 3039/IPC-650 2.4.19	psi	984,000	N/mm ²	6,784
Poisson's Ratio (MD)	ASTM D 3039/IPC-650 2.4.19		0.24		0.24
Poisson's Ratio (CD)	ASTM D 3039/IPC-650 2.4.19		0.20		0.20
Compressive Modulus	ASTM D 695 (23°C)	psi	310,000	N/mm ²	2,137
Flexural Modulus (MD)	ASTM D 790/IPC-650 2.4.4	kpsi	1,860	N/mm ²	12,824
Flexural Modulus (CD)	ASTM D 790/IPC-650 2.4.4	kpsi	1,740	N/mm ²	11,996
Peel Strength (CV1)	IPC-650 2.4.8 Sec 5.2.2 (TS)	lbs/in	8	N/mm	1.46
Thermal Conductivity (unclad)	ASTM F 433/ASTM 1530-06	W/M*K	0.65	W/M*K	0.65
Dimensional Stability (MD)	IPC-650 2.4.39 Sec. 5.4 (After Bake)	mils/in	0.21	mm/M	0.21
Dimensional Stability (CD)	IPC-650 2.4.39 Sec. 5.4 (After Bake)	mils/in	0.20	mm/M	0.20
Dimensional Stability (MD)	IPC-650 2.4.39 Sec. 5.5 (TS)	mils/in	0.15	mm/M	0.15
Dimensional Stability (CD)	IPC-650 2.4.39 Sec. 5.5 (TS)	mils/in	0.10	mm/M	0.10
Surface Resistivity	IPC-650 2.5.17.1 Sec. 5.2.1 (ET)	Mohms	2.3 x 10 ⁶	Mohms	2.3 x 10 ⁶
Surface Resistivity	IPC-650 2.5.17.1 Sec. 5.2.1 (HC)	Mohms	2.1 x 10 ⁷	Mohms	2.1 x 10 ⁷
Volume Resistivity	IPC-650 2.5.17.1 Sec. 5.2.1 (ET)	Mohms/cm	1.1 x 10 ⁷	Mohms/cm	1.1 x 10 ⁷
Volume Resistivity	IPC-650 2.5.17.1 Sec. 5.2.1 (HC)	Mohms/cm	1.8 x 10 ⁸	Mohms/cm	1.8 x 10 ⁸
CTE (x axis) (RT to 125°C)	IPC-650 2.4.41/TMA	ppm/°C	10	ppm/°C	10
CTE (y axis) (RT to 125°C)	IPC-650 2.4.41/TMA	ppm/°C	16	ppm/°C	16
CTE (z axis) (RT to 125°C)	IPC-650 2.4.41/TMA	ppm/°C	23	ppm/°C	23
Density (Specific Gravity)	ASTM D 792	g/cm ³	2.11	g/cm ³	2.11
Hardness	ASTM D 2240 (Shore D)		79		79
T _d (2% Weight Loss)	IPC-650 2.4.24.6 (TGA)	°C	526	°C	526
T _d (5% Weight Loss)	IPC-650 2.4.24.6 (TGA)	°C	551	°C	551

ET - Elevated Temperature
 HC - Humidity Conditioning
 TS - Thermal Stress

All reported values are typical and should not be used for specification purposes. In all instances, the user shall determine suitability in any given application.

TSM-DS3b Dimensionally Stable Low Loss Laminate

Designation	Dk
TSM-DS3b	3.0 ± 0.04


Available Sheet Sizes	
Inches	mm
12 x 18	305 x 457
16 x 18	406 x 457
18 x 24	457 x 610
16 x 36	406 x 914
24 x 36	610 x 914
18 x 48	457 x 1220

Typical Thicknesses*	
Inches	mm
0.0050, 0.0100, 0.0200	0.13, 0.25, 0.51
0.0300, 0.0600, 0.0900	0.76, 1.52, 2.29


*Other thicknesses in increments of 5 mils available upon request.

TSM-DS3b-R Resistor Foil Stability with Prepreg Lamination

Cumulative % Change (TSM-DS3b-R)





Cumulative % Change (EZ-IO-F-R)



Measurement Instrument and Captured Results

Agilent E8364A PNA Network Analyzer and Universal test fixture 3830 K (by ANRITSU) were used for ring resonator testing.



-R version should be used if resistive foils are being used in a manner that requires tight tolerances.

Please see our Product Selector Guide for information on available copper cladding.

An example of our part number is: **TSM-DS3b-0050-C1/C1 - 18" x 24" (457 mm x 610 mm)**

